



slarty

# FDDI



Deutsche  
Akkreditierungsstelle  
D-PL-11339-01-00

## INTERNATIONAL TESTING CENTRE

Accreditation for ISO/IEC 17025:2005 by DAKKS, Germany

Accredited by BIS India, approved by DGS&D, DGAQA, RITES, Air Headquarters, General Motors



## TEST CERTIFICATE


Supplier : Hilson Footwear Pvt. Ltd.  
Contact : Mr. Devender Kumar  
Material : Shoes  
Style No. : Synthetic Shoes for Men with PVC Sole  
Job Start Date: 01.06.2016

Job No. : 2K1605539-5  
Date of Entry: 30.05.2016  
Page : 1/1

Job Completion Date: 11.06.2016

### Laboratory Environment

Temperature  $23 \pm 2$  °C  
Relative Humidity  $50 \pm 5$  %  
The sample was conditioned for 24 hours.



TEST PROPERTY	TEST RESULT	REQUIREMENT
<b>MARKING</b>		
Size	Present	Present
Country of origin	Present	Present
Brand	Present	Present

### Bond Strength Test (Based on ISO: 17708)\*\*\*

Value 2.52 N/mm  
Requirement (Min)\* 2.50 N/mm

### Slip Resistance test (Based on SATRA TM 144: 2011)

	Forepart	Heel
Dry Condition	0.55	0.59
Wet Condition	0.50	0.51
Requirement (Min)*	0.30	0.30

### Evelet pulling (Based on EN-71-1)\*\*\*

Value 311 N  
Requirement (Min)\* 90 N

\*Requirement provided by the customer.

\*\*\*NOTE- SATRA accreditation is not applicable for above given test.

Rajesh Mishra  
(Senior Technologist)

Shailendra Saxena  
(Chief Technologist & Head Physical Laboratory)

1. This report is for technical information of the client only. Not for advertisement, promotion, publicity litigation or legal purpose.
2. This institute shall be indemnified against any dispute arising out of issue of this report.
3. Sample not drawn by FDDI and the test results relate only to the material tested.
4. The report must not be reproduced except in full without approved of FDDI.

**FOOTWEAR DESIGN & DEVELOPMENT INSTITUTE**  
**MINISTRY OF COMMERCE & INDUSTRY, GOVERNMENT OF INDIA**

A-10/A, SECTOR-24, NOIDA-201301, DISTT. GAUTAM BUDHA NAGAR (U.P.) INDIA  
Ph. : +91-120-4500128, 4500138 (Physical Lab), 4500113, 4500125 (Chemical Lab)  
EPABX : +91-120-4500100 Fax : +91-120-2412556, 2411301 Website : www.fddiindia.com